

Technical Data

Tavos Cork Wall Planks

Thickness: 3/16" Standard

Dimensions 3.9" x 36", 5.9" x 36"

Description	Test Standard	Results
Surface Burning Characteristics – Tunnel Test	E84	Class C
Surface Burning – Critical Radiant Flux	E648	Class 2
Smoke Density	ASTM E662	234 pass
Noise Reduction Coefficient (NRC)	ASTM C423-17	0.05
Sound Absorption Average (SAA)	ASTM C423-17	0.06
Acoustical Behavior STC	ASTM E90-09	52dB
Acoustical Behavior IIC	ASTM E2179-03	50 dB
Delta IIC (effect of flooring on IIC)	ASTM E2179-03	22dB
Chemical Resistance	ASTM F925	Excellent ¹
Bacterial Resistance	ASTM G21	Resistant
CHPS Indoor Air Quality Compliant	CA 01350	Yes
Resistance to Cigarette Burns	DIN 519611984	Yes
Limited Warranty		90 Day Manufacturing Defect

1. Note: Above test results are from specific materials. Variance from above values will occur due to natural variance in raw materials.